

#### MODEL Q-105 VOLTAGE 6 CAPACITY 210Ah @ 10Hr MATERIAL ABS BATTERY AGM Deep Cycle Power Battery COLOR **Brown Red** WATERING **No Watering Required**



**Q-105** 

# **6 VOLT**

#### **PHYSICAL**SPECIFICATIONS

BCI	MODEL NAME	VOLTAGE	CELL(S)	TERMINAL TYPE <sup>G</sup>	I	DIMENSIONSCINCHES	; (mm)	WEIGHT <sup>H</sup> LBS.(kg)
	0.105	c	2	M0*20	LENGTH	WIDTH	HEIGHT <sup>F</sup>	CE (20 E)
	Q-105	Ö	3	M8*20	10.24(260)	7.09 (180)	10.08 (256)	65 (29.5)

#### **ELECTRICALSPECIFICATIONS**

CRANKING PERFORMANCE		CAPACITY <sup>A</sup> MINUTES		CAPACITY <sup>B</sup> AMP-HOURS (Ah)			ENERGY (kWh)	INTERNAL RESISTANCE ( $m\Omega$ )	SHORT CIRCUIT CURRENT (amps)	
C.C.A. <sup>D</sup> @ 0°F (-18°C)	C.A. <sup>®</sup> @ 32°F (0°C)	@ 25 Amps	@ 75 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr	17	3500
_	_	470	140	190	210	230	250	1.5	1.7	

## **CHARGING INSTRUCTIONS**

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)						
SYSTEM VOLTAGE	6V 12V		24V	36V	48V	
Maximum Charge Current (A)	15% of Cs					
Absorption Voltage (2.47 V/cell)	7.4	14.8	29.6	44.4	59.2	
Float Voltage (2.30 V/cell)	6.9	13.8	27.6	41.4	55.2	

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

## **CHARGING TEMPERATURE COMPENSATION**

ADD	SUBTRACT	
0.003 volt per cell for every 1°C below 25°C 0.0017 volt per cell for every 1°F below 77°F	0.003 volt per cell for every 1°C above 25°C 0.0017 volt per cell for every 1°F above 77°F	
OPERATIONALDATA		
OPERATING TEMPERATURE	SELF DISCHARGE	
-4°F to 113°F (-20°C to +45°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 80%.	5 - 15% per month depending on storage temperature conditions .	


## **RECYCLE RESPONSIBLY**




## **STATEOF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE**

PERCENTAGE CHARGE	CELL	6 VOLT
100	2.20	6.60
90	2.17	6.51
80	2.14	6.42
70	2.12	6.36
60	2.09	6.27
50	2.07	6.21
40	2.04	6.12
30	2.02	6.06
20	2.00	6.00
10	1.97	5.91

## QUIMO Q-105 PERFORMANCE(5Hr)




## **PERCENT CAPACITY VS. TEMPERATURE(5Hr)**





Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal.

F. Batteries in storage should be charged when they decline to 75% State of Charge (SOC). G. Weight may vary.

#### BATTERY **DIMENSIONS** (shown with M8)







### **TERMINALCONFIGURATIONS** <sup>G</sup>

1	M8	2	M8
	Battery Height with Terminal in Inches (mm) 10.08 (256) Screw hole size (mm) M8*25		Bolt Size (mm) M8*20 Torque Values in-lb (Nm) 120~150 (14~17)

D.

E. Terminal images are representative only

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.
- B. The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell.
- Capacities are based on peak performance. C. Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum.





Hotline: 0513-88153000 +8618362180999 E-mail:quimobattery@163.com Website: www.quimobattery.com

Hong Kong Quimo Power Supply Co., Ltd. All rights reserved. This color pages for reference only. It is subject to change without notice. The company reserves the right to change the product design and specifications. Please check the official website of QUIMO battery (www.quimobattery.com) for the latest information.