

Q-1295

MODEL Q-1295

VOLTAGE 12

CAPACITY 212Ah @ 10Hr

MATERIAL ABS

BATTERY AGM Deep Cycle Power Battery

COLOR Brown Red

WATERING No Watering Required



12 VOLT

PHYSICAL SPECIFICATIONS

ВСІ	MODEL NAME	TERMINAL TYPE	DIMENSIONS' INCHES (mm)			WEIGHT*LBS.(kg)	HANDLES	INSTALLATION ORIENTATION
			LENGTH	WIDTH	HEIGHTF	100 (50)		
	Q-1295	M8*25	18.09(480)	7.09 (180)	9.88 (251)	128 (58)	Embedded	Vertical

ELECTRICAL SPECIFICATIONS

VOLTAGE	DLTAGE CRANKING PERFORMANCE		CAPACITY*MINUTES		CAPACITY BAMP-HOURS (Ah)			Ah)	ENERGY (kWh)	INTERNAL RESISTANCE (mΩ)	SHORT CIRCUIT CURRENT (amps)
12	C.C.A.º @0°F	C.A. [£] @32°F	@ 25 Amps	@ 56 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr	2.5	3400
12	-	_	500	198	200	212	225	237	2.85	3.5	3400

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)					
SYSTEM VOLTAGE	12V	24V	36V	48V	
Maximum Charge Current (A)	15% of C₅				
Absorption Voltage (2.47V/cell)	14.8	29.6	44.4	59.2	
Float Voltage (2.30V/cell)	13.8	27.6	41.4	55.2	

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

ADD	SUBTRACT
0.003 volt per cell for every 1°C below 25°C	0.003 volt per cell for every 1°C above 25°C
0.0017 volt per cell for every 1°F below 77°F	0.0017 volt per cell for every 1°F above 77°F

OPERATIONAL DATA

OPERATING TEMPERATURE	SELF DISCHARGE		
-4°F to 113°F (-20°C to +45°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 80%.	5 - 15% per month depending on storage temperature conditions .		

RECYCLE RESPONSIBLY









STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE

PERCENTAGE CHARGE	CELL	12 VOLT
100	2.20	13.20
75	2.13	12.78
50	2.07	12.42
25	2.01	12.06
0	1.95	11.70


QUIMO Q-1295 PERFORMANCE(5Hr)

PERCENT CAPACITY VS. TEMPERATURE(5Hr)






DIMENSIONS (shown with M8) BATTERY



TERMINALTYPE ^G



2	M8
	Bolt Size (mm) M8*20 Torque Values in-lb (Nm) 120~150 (14~17)

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.

 B. The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell.
- C. Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum.
- D. Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal.
- E. Terminal images are representative only.

 F. Batteries in storage should be charged when they decline to 75% State of Charge (SOC).

 G. Weight may vary.



